

We save / Wolf Group

www.penosil.com

Wolf Group Head Office Suur-Paala 10 13619 Tallinn Estonia

tel +372 605 9300 fax +372 605 9315 info@penosil.com

# **TECHNICAL DATA SHEET**

# PENOSIL Premium Fire Block Gun Foam 121

One-component, ready to use polyurethane gun foam for blocking passage of smoke and flames. Adheres well to most materials like wood, concrete, stone, plaster, metal, PVC and polystyrene.

- Wide application temperature range
- Perfect for hot and dry climate
- High yield
- No-bow formula
- · High thermal and acoustic insulation value

# Fields of application

- · Sealing of joints and penetrations
- Blocking the passage of smoke and flames
- Thermal and sound insulation

# **Application instructions**

#### Application conditions

Air temperature during use: +20 °F to +121 °F. Make sure the ambient temperature stays within this range until the foam has fully cured.

Can temperature during application: +41 °F to +104 °F.

#### Surface preparation

Remove dust, loose particles and oil stains from the surfaces. Moisten dry substrate with water to ensure better results. Protect adjacent surfaces with paper, plastic film or other suitable material. If needed add additional shield outside for weather protection (against rain, wind, etc.).

### Application method

Shake the can vigorously at least 20 times. Remove the cap. Hold the foam can in upright position with valve up. Screw the can tightly to the gun by holding the gun handle with one hand and turning the can with the other hand. Do not aim the gun at people. Avoid screwing the can to the gun with valve upside down. Do not screw the gun to the can. Do not bend or turn the can during screwing. Hold the can upside down when extruding the foam. Foam output can be adjusted with gun trigger and adjustment screw. Excess foam can be cut after it has fully cured.

#### <u>Cleaning</u>

Use Penosil Foam Cleaner to clean tools and surfaces from uncured foam. Hands, clothes and foam gun can also be cleaned from uncured foam with Penosil Cleaning Wipes. Remove cured foam mechanically after softening with Penosil Foam Remover.



Ne save / ///> energy / Wolf Group www.penosil.com

Wolf Group Head Office Suur-Paala 10 13619 Tallinn Estonia

tel +372 605 9300 fax +372 605 9315 info@penosil.com

### **Technical data**

Properties	Value	Unit
Tack free time (EN 17333-3)	4-7	min
Cutting time (30 mm bead, EN 17333-3)	<25	min
Fully cured in joint, 3x5cm (+73 °F)	<4	h
Curing pressure (EN 17333-2, moistened surfaces)	<3,5	kPa
Post expansion (EN 17333-2)	<60	%
Density in joint, 3x10cm (WGM106)	1519	kg/m³
Dimensional stability (EN 17333-2, moistened surfaces)	<6	%
Temperature resistance of cured product	-58+194	°F
Reaction to fire classification (EN 13501-1)	F	
Fire class of cured foam (DIN 4102-1)	B3	
Tensile strength / elongation (EN 17333-4, moistened surfaces)	>75/13	kPa / %
Compression strength (EN 17333-4, moistened surfaces)	>35	kPa
Shear strength (EN 17333-4, moistened surfaces)	>40	kPa
Thermal conductivity (EN 12667, EN 17333-5)	0,033	W/(m·K)
R-value	4,37	per inch
Sound reduction index Rst,w (EN ISO 10140)	62	dB
Foam yield in joint, 3x5 cm (WGM107), per 22 oz filling rate	17	m
Foam yield (EN 17333-1), per 22 oz filling rate	43	

The values specified were obtained at +73 °F and 50% relative humidity, unless otherwise specified. These values may vary depending on environmental factors such as temperature, moisture and type of substrates.

#### Technical classification and certificates

UL Classified

## Colour

Orange.

### **Package**

22 oz can, 12 pcs in a box.

## Storage conditions and shelf life

Guaranteed shelf life is 12 months from production date if stored in an unopened packaging in a cool and dry place at +41 °F to +86 °F. Do not expose to temperature over +122 °F, do not keep near heat sources or in direct sunlight. Store and transport in upright position. Secure cans before transport.

### Limitations

- PU foam lacks adhesion to Teflon, polyethylene, polypropylene and silicone surfaces.
- It is not advisable to unscrew the gun from the foam canister intermittently. Foam should be used in a way that the gun is screwed on once.
- Cured foam is sensitive to UV-light and direct sunlight and therefore must be covered with suitable opaque sealant, filler, paint or other material. Do not cover before foam has fully cured.
- Please observe the expiration date!

## Safety regulations

Pressurized canister. Use only in well-ventilated areas. Do not smoke during application! Use protective gear when necessary. Keep out of the reach of children. See label and safety data sheet (SDS) for more information.



www.penosil.com

Wolf Group Head Office Suur-Paala 10 13619 Tallinn Estonia

tel +372 605 9300 fax +372 605 9315 info@penosil.com

Note: The instructions in the present documentation are based on tests carried out by the manufacturer and are presented in good faith. Due to variations in materials and substrates as well as the various application possibilities that are beyond our control, the manufacturer is not liable for the results achieved. In any case, it is recommended to test the product suitability at the place of application. Manufacturer reserves the right to modify products without prior notice.

This TDS replaces and supersedes all previous data sheets on the same product.

TECHNICAL DATA SHEET
PENOSIL Premium Fire Block Gun Foam 121
Version 1