

# PENOSIL

## TECHNICAL DATA SHEET

### PENOSIL Building Silicone 322c

#### Multipurpose neutral silicone

PENOSIL Building Silicone 322c is a one-part, low modulus, high quality neutral cure silicone sealant that reacts with the atmospheric moisture, producing a flexible rubber extremely resistant. It does not contain corrosive or strong smell additives.

It preserves all properties of elasticity and adherence with no ageing problems, remaining stable in front of atmospheric agents.

#### Main benefits

- Fast curing
- High elasticity
- High movement capability
- Excellent adhesion to a wide range of substrates without priming
- UV radiation, weather and ageing resistant
- Low odour
- Non-corrosive
- Extremely long service life

#### Fields of application

- Filling, sealing, glazing, indoors and outdoors.
- Sealing high movement joints, e.g. façade joints.
- Filling and weatherproofing seams between window and door frames.
- All finishing, sanitation and ventilation sealing works.
- Important! Not suitable with natural stone.



#### Colour

According to the specific product.

#### Package

300 ml cartridge, 24 pcs in a box.  
400 ml foil package, 24 pcs in a box.  
600 ml foil package, 20 pcs in a box.

#### Storage conditions and shelf life

Guaranteed shelf life 12 months from the manufacturing date when stored in closed original package in a dry place and protected from direct sunlight at temperatures between +5 °C and +30 °C.

# PENOSIL Building Silicone 322c

## Adhering

- Concrete
- Masonry
- Brick
- Aluminium (lacquered, anodized, painted, ...)
- PVC
- Wood
- Glass
- Ceramics
- Most plastics

## Technical classifications and certificates

- Sealant for facade for interior and exterior application, suitable for use in cold climate  
EN 15651-1:2012: Type F-INT-EXT-CC
- Sealant used for sealing glazing applications, suitable for use in cold climate  
EN 15651-2:2012: Type G-CC
- ISO 11600 – F&G 25LM
- French VOC-emission class A+

# PENOSIL Building Silicone 322c

## Technical data

| Properties                      | Value           | Unit              |
|---------------------------------|-----------------|-------------------|
| Basis                           | Oxime           |                   |
| Consistency                     | Non-Slump paste |                   |
| Tack free time                  | 5...10          | minutes           |
| Skin forming time               | 10...15         | minutes           |
| Curing Rate                     | ca. 2           | mm/24h            |
| Loss of volume (ISO 10563)      | <7              | %                 |
| Resistance to flow (ISO 7390)   | 0               | mm                |
| Application temperature         | +5...+40        | °C                |
| Service temperature             | -40...+150      | °C                |
| Movement capability (ISO 11600) | ±25             | %                 |
| Elastic recovery (ISO 7389)     | >80             | %                 |
| Shore A hardness (ISO 868)      | ca. 27          |                   |
| E-Modulus 100% (ISO 37)         | 0,50            | N/mm <sup>2</sup> |
| Tensile strength (ISO 37)       | 1,40            | N/mm <sup>2</sup> |
| Elongation at break (ISO 37)    | >500            | %                 |
| E-Modulus 100% (ISO 8339)       | 0,40            | N/mm <sup>2</sup> |
| Tensile strength (ISO 8339)     | 0,60            | N/mm <sup>2</sup> |
| Elongation at break (ISO 8339)  | 250             | %                 |
| Density (EN-ISO 2811-1)         | ca. 1,23        | g/ml              |
| VOC content (SCAQMD rule 1168)  | ca. 58          | g/l               |

The parameters indicated have been measured at +23 °C and 50% relative air humidity.

## Application instructions

### Application conditions

Application temperature between +5 °C and +40 °C.

### Surface preparation

The surfaces must be dry, clean from dust, loose particles and oil. Non-porous surfaces should be cleaned with solvent and a clean, non-fluffy cotton cloth. Solvent excess should be removed before evaporating with a clean cloth.

# PENOSIL Building Silicone 322c

## Application method

**Cartridge:** cut off the threaded end of the cartridge and screw on the application nozzle for directing sealant. Cut the threaded end in a way where a suitable opening for application is produced. Place the cartridge together with the applicator in the gun and fill the installation nozzle with sealant, by repeatedly pressing the gun trigger.

**Foil package:** open the end of the foil pack and place the pack inside the gun so that the dosing nozzle keeps covering its open portion. Place the dosing nozzle on the open end and screw on the cap to close the tube. Cut the nozzle to create a suitable opening for dosing sealant.

Apply sealant in the joint by repeatedly and evenly pressing on gun trigger and smoothly dragging the nozzle along the joint. After application, smooth the surface with a suitable tool (e.g., spatula) and remove excess material.

If necessary, the adjacent surfaces of the joint should be protected to avoid staining. Usually, masking tape is used for this.

Protective masking tapes should be removed before the sealant's skin is formed.

In wider and movable joints, backer rod should be used as a back-up material, to ensure the correct thickness and shape of sealant joint and to avoid three-sided adhesion.

Ensure adequate ventilation in all joint locations. During the curing process, make sure that no impurities can settle on the surface and that the joint surface is not affected by mechanical load.

## Cleaning

Uncured sealant can be cleaned with solvents like white spirit, acetone or with PENOSIL Cleaning Wipes. Cured sealant can be removed mechanically. If needed silicone remover should be used.

## Limitations

- Do not use on bituminous substrates or on building materials which might bleed oils, plasticizers or solvents (e.g. natural rubber, chloroprene, EPDM, ...)
- There is no adhesion to PE, PP, PTFE (Teflon®).
- Cannot be overpainted.
- Not intended for structural glazing.
- Due to the wide variety of possible substrates, we recommend a preliminary compatibility and adherence test. If necessary, prime surfaces to improve adhesion.
- Due to the wide variety of influences during and after application, the customer must always test the product first.
- Please observe the expiration date!

## Safety regulations

Ensure sufficient ventilation during application and wear necessary personal protective equipment.

More specific safety information is available on the safety data sheet (SDS).

Note: The instructions in the present documentation are based on tests carried out by the manufacturer and are presented in good faith. Due to variations in materials and substrates as well as the various application possibilities that are beyond our control, the manufacturer is not liable for the results achieved. In any case, it is recommended to test the product suitability at the place of application. Manufacturer reserves the right to modify products without prior notice.

This TDS replaces and supersedes all previous data sheets on the same product.

## PENOSIL Building Silicone 322c

08-07-2026 12:51:23

Wolf Group Head Office  
Suur-Paala 10  
13619 Tallinn  
Estonia

Tel +372 605 9300  
Fax +382 605 9315  
info@penosil.com